

XL-0854

100% SYNTHETIC TIRE & PAD LUBRICANT WITH GRAPHITE FOR ROTARY KILNS

XL-0854 is a custom blend of **synthetic polymers** and performance enhancing additives expressly designed to slowly evaporate at high temperatures leaving **absolutely no abrasive residues**.

XL-0854's specially formulated additives including **high concentrations of solid boundary lubricants** are designed to lubricate tires and pads under the most severe and critical operating conditions.

XL-0854 Will reduce friction, thereby reducing:

- Tire & pad wear
- Kiln "creepage"
- Flexing of the kiln shell
- Shell ovality
- Replacement of tire shell sections

XL-0854 has been used successfully at operating temperatures from -40°C to 600°C.

TYPICAL SPECIFICATIONS					
Product Code: XL-0854	/000	/001	/002	/003	/004
N.L.G.I. Grade:	0	1	2	3	4
Penetration @ 25°C (ASTM D-217)	360	365	265	240	180
After 60 strokes	365	331	268	240	185
After 10,000 strokes	367	335	273	247	185
After 60,000 strokes	372	343	275	255	200
Dropping Point (°C) (ASTM D-2265)			None		
Melting Point (°C)			None		
Copper Strip Test (163°C for 3 hours) (ASTM D-130)			Negative		
Texture			Adhesive/Tacky		
Colour			Black		
Timken OK Load (kg/lbs) (ASTM D-2509)	40/90	40/90	40/90	40/90	40/90
Type of thickener			Inorganic		
Oil Separation (24hrs @ 25°C) (ASTM D-1742)	< 1%	< 1%	< 1%	< 1%	< 1%
Additives		Graphite, Anti-rust, Anti-corrosion			
Temperature Range (°C)			-40 to 600		
Maximum Intermittent Temperature (°C)			650		
Minimum Temperature (°C)	-40	-40	-30	-15	0

TYPICAL SPECIFICATIONS					
Base Oil Viscosity (cSt @ 100°C) (ASTM D-445)			200		