

## XL-0925

### HYBRID SYNTHETIC GREASE DGG

**XL-0925** is a unique 100% hybrid synthetic oil-based, hydrophobic bearing grease formulated to withstand extremely high static pressures at very low and intermittent RPM.

The blend of synthetic base oils and performance enhancing additives selected to formulate **XL-0925** were chosen for their individual inherent chemical and physical characteristics. Priority attributes were assigned to **endurance**, **non-toxicity**, and **biodegradability** in aqueous environments.

The exceptionally high base-oil viscosity index (VI) and low temperature fluidity enables **XL-0925** to provide efficient lubrication over a wide range of temperature, from -50°C to 200°C.

Low and intermittent bearing RPM inhibits the ability of most conventional lubricants (greases) to form a stable lubricating elasto-hydrodynamic (EHD) film. Under heavy loads, rollers will come in contact with the bearing race rings, and scoring will occur upon initial rotation, unless an appropriate boundary lubricant protects contacting metallic surfaces.

Unlike conventional lubricants, **XL-0925** has been designed to perform like a “lubricant sponge” releasing a **non-toxic** and **chemically inert** graphite film to be deposited on the contact areas of friction, providing the necessary lubrication to the rollers. Excess graphite will be re-absorbed into the “lubricant sponge” once the roller has passed over the surface.

**XL-0925** is formulated for use in sluice gates, intake gates, and any other application requiring a non-toxic, partially biodegradable, hydrophobic EP grease in high loaded bearings.

TYPICAL SPECIFICATIONS			
Product Code: XL-0925	/102		/202
N.L.G.I. Grade:	2		2
Penetration @ 25°C (ASTM D-217)			
After 60 strokes	268		265
After 10,000 strokes	290		305
Dropping Point (°C) (ASTM D-2265)	None		None
Melting Point (°C)	None		None
Copper Strip Test (163°C for 3 hours)	Negative		Negative
Texture		Smooth/tacky	
Colour		Dark gray	
Type of thickener		Silica	

<b>TYPICAL SPECIFICATIONS</b>			
Oil Separation (24hrs @ 25°C) (ASTM D-1742)	< 1%		< 1%
Additives		Carbon/Graphite	
Temperature Range (°C)		-50 to 200	
Minimum Dispensing Temperature (°C)	-66		-62
Maximum Intermittent Temperature (°C)	250		250
Base Oil Viscosity (cSt @ -30°C) (ASTM D-445)	39,700		20,300
Base Oil Viscosity (cSt @ 0°C) (ASTM D-445)	7,450		3,000
Base Oil Viscosity (cSt @ 30°C) (ASTM D-445)	3,000		800
Base Oil Viscosity (cSt @ 40°C) (ASTM D-445)	2,100		600
Base Oil Viscosity (cSt @ 100°C) (ASTM D-445)	440		105
Base Oil Viscosity Index	378		273