

XL-2350

FAST DRYING FILM LUBRICANT WITH MOLYBDENUM

XL-2350 offers excellent extreme pressure dry film lubrication. This specially processed long-wearing molybdenum disulfide coating material air dries at room temperatures in five to ten minutes.

ADVANTAGES:

- Low coefficient of friction –
- Excellent adhesion to most substrates, especially metals.
- Thin film – 0.003 to 0.005 in. (0.008 to 0.013 millimetres).
- Excellent release properties.
- Minimum surface pre-treatment.
- Easy application.
- Fast room temperature cure.

XL-2350 can be applied to all substances not affected by the fluid component Trichloroethylene: stainless steel, copper, alloys, rubber and plastics.

PHYSICAL PROPERTIES	
XL-2350 (as supplied)	
Lubricant:	Molybdenum Disulfide
Fluid Component:	Trichloroethylene
Colour:	Dark grey
Shelf Life:	One year
XL-2350 (when cured)	
Coefficient of Friction:	0.23 (static)
Service Temperature (°C):	315
Intermittent Temperature (°C):	660