

## XL-2353

### MEDIUM DRYING FILM LUBRICANT WITH MOLYBDENUM

**XL-2353** offers excellent extreme pressure dry film lubrication. This specially processed synthetic / solvent-based long-wearing molybdenum disulfide coating material dries slowly at elevated temperatures.

#### ADVANTAGES

- Low coefficient of friction
- Excellent release properties.
- Minimum surface pre-treatment.
- Easy application.

**XL-2353** can be applied to all substances not affected by the Mineral Spirits fluid component, or the Polyolester carrier oil.

PHYSICAL PROPERTIES	
<b>XL-2353 (as supplied)</b>	
Lubricant:	Polyolester, Molybdenum Disulfide
Fluid Component:	Mineral Spirits
Colour:	Dark grey
Shelf Life:	One year
<b>XL-2353 (when cured)</b>	
Coefficient of Friction:	0.23 (static)
Service Temperature (°C):	315
Intermittent Temperature (°C):	660