

XL-2353

MEDIUM DRYING FILM LUBRICANT WITH MOLYBDENUM

XL-2353 offers excellent extreme pressure dry film lubrication. This specially processed synthetic / solvent- based long-wearing molybdenum disulfide coating material dries slowly at elevated temperatures.

ADVANTAGES

- Low coefficient of friction
- Excellent release properties.
- Minimum surface pre-treatment.
- Easy application.

XL-2353 can be applied to all substances not affected by the Mineral Spirits fluid component, or the Polyolester carrier oil.

PHYSICAL PROPERTIES	
XL-2353 (as supplied)	
Lubricant:	Polyolester, Molybdenum Disulfide
Fluid Component:	Mineral Spirits
Colour:	Dark grey
Shelf Life:	One year
XL-2353 (when cured)	
Coefficient of Friction:	0.23 (static)
Service Temperature (°C):	315
Intermittent Temperature (°C):	660